

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification 5 :</b> C03C 25/02, C08J 5/08 G02B 6/44	<b>A1</b>	<b>(11) International Publication Number:</b> WO 91/15434 <b>(43) International Publication Date:</b> 17 October 1991 (17.10.91)
<b>(21) International Application Number:</b> PCT/US91/01871 <b>(22) International Filing Date:</b> 22 March 1991 (22.03.91)  <b>(30) Priority data:</b> 501,829 30 March 1990 (30.03.90) US  <b>(71) Applicant:</b> OWENS-CORNING FIBERGLAS CORPORATION [US/US]; Fiberglas Tower - T/26, Toledo, OH 43659 (US).  <b>(72) Inventors:</b> ADZIMA, Leonard, Joseph ; 40 Faneuil Hall Road, Pickerington, OH 43147 (US). HAGER, Thomas, Paul ; 197 Sassafra Way, Westerville, OH 43081 (US). FLAUTT, Martin, Charles ; 230 Knoll Drive, Granville, OH 43023 (US).		<b>(74) Agents:</b> PACELLA, Patrick, P. et al.; Fiberglas Tower - T/26, Toledo, OH 43659 (US).  <b>(81) Designated States:</b> AU, BE (European patent), BR, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FI, FR (European patent), GB (European patent), IT (European patent), JP, KR, NL (European patent), NO, SE (European patent).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> COATING COMPOSITION FOR FIBERS  <b>(57) Abstract</b> <p>An aqueous coating composition for fibers comprising a thermoplastic polymer powder, a surfactant, a film former polymer, a thickening agent, the balance being water. When coated onto a bundle or strand of glass fibers the coated glass fibers have a final solids content range from about 25 - 30 weight percent and have good flexibility and good compressive strength. Optical fibers are wrapped with coated continuous filaments and then coated with an extruded layer of a thermoplastic resin.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TC	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark				

5

-1-

DESCRIPTION

10

**COATING COMPOSITION FOR FIBERS**TECHNICAL FIELD

15 This invention relates to impregnant or coating compositions for fibers. The coating compositions of the present invention are especially useful for coating continuous glass strands for use as an overwrap on a fiber optical cable.

BACKGROUND ART

20

The use of coating compositions on fibers is well known and coating compositions are applied to the surface of the fibers for several reasons. While coating compositions are usually applied to the fibers for the purpose of protecting the fibers during processing subsequent to their formation, such compositions can also have incorporated into their compositions certain components which impart properties which facilitate their usage. Such properties which can be improved include impact strength, compressive strength, strand integrity, flexibility, toughness, and improved adherence between the fiber and a matrix resin.

30

Such coated fiber are useful in overcoating or wrapping fibers or cables such as, for example, optical cables. Typically, glass fibers are used as an overwrap on a cable or fiber and a thermoplastic resin is solidified on the glass fibers typically by an extruded overcoat. There is no adhesion between the extruded jacket and the braided, helically wound or otherwise applied overwrap. While installing a

35

-2-

5 cable, grips are attached to the ends of the cable. Due to the poor adhesion between the braided glass overwrap and the extruded coating the grips tend to pull the extruded coating off the cable. The use of the thermoplastic impregnated strands, according to the present invention, prevents this by adhering to the extruded overcoat.

10 An object of the present invention is to provide a slurry or coating composition for coating glass fibers useful as an overwrap or coating on cables or fibers. It is a further object to provide a coating composition which does not suffer the drawbacks of conventionally coated fibers. In cables currently produced special members are  
15 required to prevent buckling. These members are expensive and difficult to use. The thermoplastic impregnated overwrap of the present invention becomes the anti-buckling member after it is fused. It is still a further object to provide a coating composition which can be totally bound to an extruded protective coating which typically  
20 surrounds the cable or fiber.

#### DISCLOSURE OF INVENTION

The present invention provides an aqueous coating composition useful for glass strands which comprises a thermoplastic resinous  
25 dispersion with a film forming polymer.

The coating of the present invention comprises: a thermoplastic resin (preferably polyethylene polymer powder), a surfactant, a film forming polymer (preferably a polyurethane latex polymer), a gel or thickening agent, the balance being water.

30 According to one preferred use of the present invention, the thermoplastic resin polymer is suspended in the aqueous coating composition in the powdered form when coated on a bundle or strand of fibers or filaments. The coated strand is then wrapped around a cable or core. After the cable or core has been wrapped with the  
35 strand, a thermoplastic jacket is extruded over the top of the cable or core. The heat of the molten polymer causes the thermoplastic

-3-

5 polymer powder in the overwrap to melt and flow. The strand can also be preheated prior to the extrusion of the thermoplastic jacket to provide a more complete fusion of the powdered polymer on the overwrap. Upon cooling, the wrapped cable stiffens imparting anti-buckling and stiffness to the cable without adding a separate stiffness member.

10 The present invention achieves a desirable cable without the need to use self crosslinking resinous materials to provide partial curing or to reduce tackiness of the coating. The present invention further does not require the use of any lubricants.

15 The aqueous coating composition is especially useful in impregnating continuous glass strands in conventional in-line or off-line coating processes.

20 These and other aspects and advantages of the present invention will become more clear after consideration is given to the detailed description of the invention which follows.

#### BEST MODE OF CARRYING OUT INVENTION

25 The present invention is employable with any glass fiber conventionally utilized for the reinforcement of polymeric resins. The term "glass fibers" as used herein shall mean filaments formed by attenuation of one or more streams of molten glass and to strands formed when such glass fiber filaments are gathered together in forming. The term shall also mean yarns and cords formed by applying and/or twisting a multiplicity of strands together and to  
30 woven and non-woven fabrics which are formed of such glass fiber strands, yarns, or cords. Preferably, the coating formulation of the present invention is usable with conventionally available fibers.

35 The glass fibers used as input to an off-line process can be sized with any conventionally known sizing composition, which is well known to those skilled in the art.

The individual components utilized in the practice of this invention are commercially available and can thus be simply blended

-4-

5 with one another in the preparation of the formulations embodying the features of the present invention.

The invention comprises an aqueous coating composition comprising, approximately, on a weight percent basis:

	Weight percent
10 thermoplastic polymer powder	5 - 50
surfactant	.5 - 1.5
film former polymer	.5 - 5
a thickening agent	0 - .1
water	balance

15 Final solids content ranges from 6 to 56 weight percent. The coating composition is applied so as to deposit a dried coating on the fibers corresponding to about 5 to 50 weight percent of the weight of the fibers (LOI).

20 Preferably the aqueous coating composition comprising, approximately, on a weight percent basis:

	Weight percent
thermoplastic polymer powder	18 - 24
surfactant	.75 - 1.0
film former polymer	1 - 3
a thickening agent	0 - .05
25 water	balance

30 Final solids content ranges from 20 to 28 weight percent. The coating composition is applied so as to deposit a dried coating on the fibers corresponding to about 24 to 30 weight percent of the weight of the fibers (LOI).

35 The thermoplastic resin used in the aqueous coating composition may be selected from among conventional thermoplastic resin powders such as, for example, polyesters, polyethylenes, polypropylenes, polyamides and other such conventional polymers available in a powdered form. The particle size of these powdered polymers should be less than 100 microns. One such material is a

-5-

5 polyethylene polymer, Microthene FN 510 R available from USI  
Chemicals Co. In a preferred embodiment the average particle size  
of the thermoplastic powder is in the range of about 20 microns or  
less. It is desired that the resins useful for coating cables (especially  
optical fibers) have good impact strength, a high modulus of  
elasticity, good flexibility, and good adhesion to polyethylene and  
10 PVC jacketing materials.

The surfactant used in the aqueous coating composition may be  
a conventional polyether polyol, such as, for example an alkyl aryl  
polyether alcohol sold by the trade name TRITON X 100 R available  
from the Rohm & Haas Co.

15 The dispersible or emulsifiable film forming polymer used in  
the aqueous coating composition may be a conventional elastomeric  
polyurethane polymer, such as, for example, RUCO 2010 L available  
from the RUCO Polymer Corp.

20 The gel or thickening agent used in the aqueous coating  
composition may be chosen from a wide range of conventional  
thickening agents. Drewfloc 270, a polyamide from Drew Chemical  
Co., has been found to be particularly useful in this application.

The amount of water in the aqueous coating composition is that  
amount necessary to give a total solids (nonaqueous) content of the  
25 aqueous coating composition sufficient to coat the fibers. It is  
preferred to have the total solids content in the range of about 5 to  
50 weight percent, most preferably about 20-28 weight percent.

In the preferred method of formulation of the aqueous coating  
composition, the surfactant is dissolved in about three fourths of the  
30 water forming a main mixture. The thermoplastic resin powder is  
dispersed into the main mixture. The film forming polymer is then  
added directly to the resulting main mixture. The thickening agent is  
dissolved in the remaining water, and thereafter added to the main  
mixture. The resulting aqueous coating composition has a good  
35 consistency, low viscosity, and good stability.

-6-

5 The aqueous coating composition can be applied to continuous  
strand glass fibers in conventional off-line or in-line processes. In  
the in-line process the coating is applied as a sizing in the fiber  
forming operation. In the off-line process a bundle of input strands  
of glass fibers are pulled through an impregnation bath comprising  
the aqueous coating composition. The excess coating composition is  
10 removed by a stripper die. The resulting wet impregnated or coated  
bundle is dried in a conventional manner. The coated glass strands  
may be dried at elevated temperatures in an oven by any of the  
processes known to those skilled in the art to remove a substantial  
amount of the water. They may also be dried using a dielectric oven.  
15 The drying of the coated glass strand at elevated temperatures does  
not melt or fuse the thermoplastic resin. The thermoplastic resin is  
held to the glass fiber by the film forming polymer.

In one process a package is formed by taking up the dry or  
nearly dry strand on a winder. The package typically has a 5-20  
20 percent by weight residual moisture. Further moisture is then  
removed by oven drying the package. The oven temperature must be  
below the melting point of the powdered polymer. The resultant  
coated strand is plyable and has excellent powder holding capability.

25 The coated glass fiber is especially useful as an overwrap on  
any type of cable, or on a fiber optic cable. It is also within the  
contemplated scope of the present invention that the coated glass  
fiber can be used in any of a number of reinforcement products. The  
coated glass fiber is overwrapped on a cable or fiber in a manner  
known to those skilled in the art.

30 A glass fiber coated with the aqueous coating composition of  
the present invention is superior to the conventionally coated or  
otherwise sized fibers currently available since the coated glass  
fibers have a desirably higher loading content of thermoplastic resin  
powder. The glass strand, as coated, is flexible, and is as easily  
35 processed as conventionally sized glass fibers.



-7-

5 It is also within the contemplated scope of the present  
invention that such overwrapped cable have a secondary coating or be  
further coated with an extrusion of some type of thermoplastic resin  
such that the thermoplastic resin on the glass fibers not only fuses  
together with itself, but also is totally bound with the secondary  
thermoplastic coat. This then provides a coated glass fiber which  
10 behaves both as a tension member and as a compression member. As  
a compression member the glass fiber overwrap on the cable serves  
as an antibuckling element to prevent damage to the core fiber or  
cable during processing, installation or in-use curing temperature  
cycling, especially cold temperature exposures ( $-40^{\circ}\text{C}$ ).  
15

### INDUSTRIAL APPLICABILITY

#### EXAMPLE I

20 An inventive coating composition prepared from the following  
ingredients:

	Weight
percent	
thermoplastic polymer powder, Microthene FN 510 from USI Chemicals Co.	25
25 alkyl aryl polyether alcohol surfactant TRITON X100 from Rohm & Haas	0.89
polyurethane latex film forming polymer RUCO 2010 L from RUCO Polymer Corp.	2.0
30 poly acrylamide thickening agent, Drewfloc 270 from Drew Chemical Co.	.048
water	balance

Final solids content was about 27 weight percent. The coating  
35 composition is applied onto a conventionally sized glass, here an H-15  
762 sized glass available from Owens-Corning Fiberglas Corporation

-8-

5 so as to deposit a dried coating on the fibers corresponding to about 26 weight percent of the weight of the fibers (LOI).

Heating the coated fibers to about 150°C causes the adhered thermoplastic resin to flow and fuse, thereby producing a fiber reinforced product especially suitable for use as a coating or overwrap for a cable or fiber. The coated, cured fiber reinforced  
10 product when overwrapped on a cable provides a cable having the necessary flexibility and proper degree of stiffness for subsequent processing.

The fiber reinforced optical fiber or cable can have a secondary coating comprising, for example a thermoplastic resinous material  
15 which further protects the optical fiber. In a preferred embodiment the thermoplastic resinous material of the secondary coating is essentially the same thermoplastic resinous material used in the aqueous coating composition.

While the invention has been described in detail and with  
20 reference to specific embodiment thereof, it will be apparent to one skilled in the art that various changes and modification can be made therein without departing from the spirit and scope thereof.

25

30

35

5

-9-

10 CLAIMS

1. An aqueous coating and impregnant composition consisting essentially of, on a weight percent basis:

		Weight percent
	thermoplastic polymer powder	5 - 50
15	surfactant	.5 - 1.5
	film former polymer	.5 - 5
	a thickening agent	0 - .1
	water	balance

20 2. The aqueous coating composition of claim 1 having a final solids content ranging from 6 to 56 weight percent.

3. An aqueous coating and impregnant composition consisting essentially of, on a weight percent basis:

		Weight percent
25	thermoplastic polymer powder	18 - 24
	surfactant	.75 - 1.0
	film former polymer	1 - 3
	a thickening agent	0 - .05
30	water	balance

4. The aqueous coating composition of claim 3 having a final solids content ranging from 20 - 28 weight percent.

35 5. An aqueous coating and impregnant composition consisting essentially of, on a weight percent basis:

-10-

		Weight percent
5	thermoplastic polymer powder	25
	surfactant	0.89
	film former polymer	2.0
	a thickening agent	.048
10	water	balance

6. The aqueous coating composition of claim 5 having a final solids content of about 27 weight percent.

15 7. A plurality of flexible filaments at least a portion of the filament's surface being coated with a residue produced by evaporating water from the aqueous coating composition of claim 1.

20 8. A filament according to claim 7 wherein the filament is made of glass.

25 9. A wrapped optical glass fiber comprising a layer of a reinforcing material substantially covering an optical glass fiber, the reinforcing material comprises continuous filaments coated with a residue produced by evaporating water from the aqueous coating composition of claim 1.

30 10. The optical glass fiber of claim 9 wherein the wrapped fiber has coated thereon an extruded layer of a thermoplastic resin material.

35 11. The optical glass fiber of claim 10 wherein the extruded layer of thermoplastic resin material is essentially the same thermoplastic resin as the thermoplastic polymer powder in the aqueous coating composition.

-11-

5       12. The aqueous coating composition according to claim 1  
wherein the thermoplastic polymer is a polyethylene polymer in the  
powdered form.

10       13. The aqueous coating composition according to claim 1  
wherein the surfactant is an aryl alkyl polyether alcohol.

14. The aqueous coating composition according to claim 1  
wherein the film former polymer is a polyurethane latex polymer.

15       15. The aqueous coating composition according to claim 1  
wherein the thickening agent is a polyacrylamide.

20

25

30

35

# INTERNATIONAL SEARCH REPORT

International Application No PCT/US 91/01871

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (if several classification symbols apply, indicate all) <sup>5</sup> According to International Patent Classification (IPC) or to both National Classification and IPC IPC5: C 03 C 25/02; C 08 J 5/08, G 02 B 6/44														
<b>II. FIELDS SEARCHED</b> <div style="text-align: right; font-size: small;">Minimum Documentation Searched<sup>7</sup></div> <table style="width: 100%; border: none;"> <tr> <td style="width: 20%; border: none; vertical-align: top;">Classification System</td> <td style="border: none;">Classification Symbols</td> </tr> <tr> <td style="border: none; vertical-align: top; padding-top: 10px;">IPC5</td> <td style="border: none; padding-top: 10px;">C 03 C; C 08 J; C 08 L; C 09 D; G 02 B</td> </tr> </table> <div style="text-align: center; font-size: x-small; margin-top: 5px;">Documentation Searched other than Minimum Documentation to the extent that such Documents are included in Fields Searched<sup>8</sup></div>			Classification System	Classification Symbols	IPC5	C 03 C; C 08 J; C 08 L; C 09 D; G 02 B								
Classification System	Classification Symbols													
IPC5	C 03 C; C 08 J; C 08 L; C 09 D; G 02 B													
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT<sup>9</sup></b> <table border="1" style="width: 100%; border-collapse: collapse; font-size: x-small;"> <thead> <tr> <th style="width: 10%;">Category *</th> <th style="width: 60%;">Citation of Document,<sup>11</sup> with indication, where appropriate, of the relevant passages<sup>12</sup></th> <th style="width: 30%;">Relevant to Claim No.<sup>13</sup></th> </tr> </thead> <tbody> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td>EP, A1, 0062138 (CHEMISCHE WERKE HÜLS AG) 13 October 1982, see the whole document  --</td> <td style="text-align: center; vertical-align: top;">1-6, 12-15</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td>DE, B2, 2024477 (PPG INDUSTRIES, INC.) 26 October 1978, see the whole document  --</td> <td style="text-align: center; vertical-align: top;">1-8, 12-15</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td>Patent Abstracts of Japan, Vol 10, No 28, C326, abstract of JP 60-180938, publ 1985-09-14 (FURUKAWA DENKI KOGYO K.K.)  -- -----</td> <td style="text-align: center; vertical-align: top;">9-11</td> </tr> </tbody> </table>			Category *	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>	A	EP, A1, 0062138 (CHEMISCHE WERKE HÜLS AG) 13 October 1982, see the whole document  --	1-6, 12-15	A	DE, B2, 2024477 (PPG INDUSTRIES, INC.) 26 October 1978, see the whole document  --	1-8, 12-15	A	Patent Abstracts of Japan, Vol 10, No 28, C326, abstract of JP 60-180938, publ 1985-09-14 (FURUKAWA DENKI KOGYO K.K.)  -- -----	9-11
Category *	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>												
A	EP, A1, 0062138 (CHEMISCHE WERKE HÜLS AG) 13 October 1982, see the whole document  --	1-6, 12-15												
A	DE, B2, 2024477 (PPG INDUSTRIES, INC.) 26 October 1978, see the whole document  --	1-8, 12-15												
A	Patent Abstracts of Japan, Vol 10, No 28, C326, abstract of JP 60-180938, publ 1985-09-14 (FURUKAWA DENKI KOGYO K.K.)  -- -----	9-11												
<div style="display: flex; justify-content: space-between; font-size: x-small;"> <div style="width: 45%;"> <p>* Special categories of cited documents:<sup>10</sup></p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance, the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"Z" document member of the same patent family</p> </div> </div>														
<b>IV. CERTIFICATION</b> <table style="width: 100%; border: none;"> <tr> <td style="width: 50%; border: none; vertical-align: top;">           Date of the Actual Completion of the International Search             20th June 1991         </td> <td style="width: 50%; border: none; vertical-align: top;">           Date of Mailing of this International Search Report             17. 07. 91         </td> </tr> <tr> <td style="border: none; vertical-align: top;">           International Searching Authority             EUROPEAN PATENT OFFICE         </td> <td style="border: none; vertical-align: top;">           Signature of Authorized Officer   <div style="display: flex; align-items: center;"> <div style="border: 1px solid black; padding: 2px 5px; margin-right: 10px;">M. PEIS</div> <div style="font-family: cursive; font-size: 1.2em;">M. Peis</div> </div> </td> </tr> </table>			Date of the Actual Completion of the International Search  20th June 1991	Date of Mailing of this International Search Report  17. 07. 91	International Searching Authority  EUROPEAN PATENT OFFICE	Signature of Authorized Officer  <div style="display: flex; align-items: center;"> <div style="border: 1px solid black; padding: 2px 5px; margin-right: 10px;">M. PEIS</div> <div style="font-family: cursive; font-size: 1.2em;">M. Peis</div> </div>								
Date of the Actual Completion of the International Search  20th June 1991	Date of Mailing of this International Search Report  17. 07. 91													
International Searching Authority  EUROPEAN PATENT OFFICE	Signature of Authorized Officer  <div style="display: flex; align-items: center;"> <div style="border: 1px solid black; padding: 2px 5px; margin-right: 10px;">M. PEIS</div> <div style="font-family: cursive; font-size: 1.2em;">M. Peis</div> </div>													

ANNEX TO THE INTERNATIONAL SEARCH REPORT  
ON INTERNATIONAL PATENT APPLICATION NO.PCT/US 91/01871

SA 46096

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.  
The members are as contained in the European Patent Office EDP file on 30/04/91  
The European Patent office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A1- 0062138	13/10/82	DE-A- 3111902	07/10/82
DE-B2- 2024477	26/10/78	BE-A- 750649	20/11/70
		FR-A-B- 2044805	26/02/71
		GB-A- 1286725	23/08/72
		NL-A- 7006976	24/11/70
		SE-B- 359808	10/09/73
		US-A- 3655353	11/04/72
		US-A- 3814715	04/06/74

For more details about this annex: see Official Journal of the European patent Office, No. 12/82